



#203 NON-FIBERED ROOF & FOUNDATION COATING

TROPICAL ROOFING PRODUCTS' #203 NON-FIBERED ROOF & FOUNDATION COATING is a non-fibered liquid asphalt waterproofing. #203 is excellent for adhering rock or roofing granules and provides a tough durable shield against the elements and gives protection against leaks when properly applied. It provides a longer lasting and thicker coating than hot asphalt without the disagreeable odor or smoke. #203 requires less labor and equipment, provides a stronger, more reliable roof and eliminates the hazards of using hot asphalt. #203 minimizes the risk of wrinkles, blisters and other problems often associated with overheated or underheated asphalt and is more flexible than hot asphalt in cold weather.

PREPARATION: All surfaces must be clean, dry, smooth, even and free from all other foreign matter. Raised edges, buckles and blisters should be cut and flattened. Check flashings, drains, edgings, vents, and valleys and repair as needed.

APPLICATION: Apply to clean dry surface using stiff, bristle brush, roller, or spray equipment. For best results, weather should be at least 65°F, dry and clear, with no threat of rain for 48 hours. Drying time is approximately 48 hours in warm, dry weather.

COVERAGE: Apply at the rate of approximately 2 to 3 gallons per 100 sq. ft. depending on job specifications. Stir coating to uniform consistency before using. Avoid heavy mounds of mass accumulation.

PRECAUTIONS: DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. USE ONLY WITH ADEQUATE VENTILATION! Avoid contact with skin and breathing of vapor. CLOSE AIR INTAKES on roof until solvents dissipate. KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 250 G/L
CONSISTENCY — Thick Black Liquid
WEIGHT — 8.0 lbs. per gal +/- .2
FLASH POINT (T.C.C.) — 105°F+
DRYING TIME — Average: 2-5 hrs. to touch

www.tropicalroofingproducts.com



FLORIDA
1904 SW 31st Ave.
Hallandale, FL 33009
fax: 954.963.2033
toll-free: 800.432.2855

CALIFORNIA
14435 Macaw Street
La Mirada, CA 90638
fax: 714.670.1605
toll-free: 877.827.2622

TEXAS
1225 Brai Drive, P.O. Box 5335
Port Arthur, TX 77640
fax: 409.727.4647
toll-free: 866.727.0091