



#2100 ALL WEATHER PREMIUM RUBBERIZED FLASHING CEMENT

TROPICAL ROOFING PRODUCTS' #2100 All Weather Premium Rubberized Flashing Cement is an unsurpassed, top notch flashing compound. #2100 is manufactured with high-grade oxidized asphalts for a true cure. #2100 remains resilient and flexible with its high SBS rubber content. Special surfactants make this product adhere to any solid surface in any climate – wet or dry. There are no fillers or extenders of any type. #2100 will not run, slip, sag, or mudcrack under any conditions.

PREPARATION: Surface must be clean and free from rust or any other foreign matter that would interfere with a good bond. For best results in cold weather, store at room temperature for 24 hours prior to application.

APPLICATION: Use a trowel, putty knife or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1/8" to 1/4" thick. Apply and work cement into break or crack, then apply cement 2"-4" beyond the problem area feathering the edges. Embed fabric to reinforce cement, then cover with additional cement, if problem area is over 1/4" wide or 2" long.

COVERAGE: Apply at a minimum rate of 1/8" (32mm). Approximate coverage 12-20 square feet per gallon.

PRECAUTIONS: DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. USE ONLY WITH ADEQUATE VENTILATION! Avoid contact with skin and breathing of vapor. CLOSE AIR INTAKES on roof until solvents dissipate. KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 250 G/L

CONSISTENCY — Thick Mastic, Apply by Trowel
WEIGHT — 8.7 lbs. per gal
FLASH POINT (T.C.C.) — 105°F+
SERVICE TEMPERATURE (Range) — 40°F-90°F
RESISTANCE TO ACIDS, ALKALYS — Excellent

ASTM
D-4586
D-3409

www.tropicalroofingproducts.com



FLORIDA
1904 SW 31st Ave.
Hallandale, FL 33009
fax: 954.963.2033
toll-free: 800.432.2855

CALIFORNIA
14435 Macaw Street
La Mirada, CA 90638
fax: 714.670.1605
toll-free: 877.827.2622

TEXAS
1225 Brai Drive, P.O. Box 5335
Port Arthur, TX 77640
fax: 409.727.4647
toll-free: 866.727.0091

MIAMI-DADE COUNTY
APPROVED
NOA#: 06-0119.03
Exp: 8/23/11

