



#2200 RUBBERIZED ALUMINUM FLASHING CEMENT

TROPICAL ROOFING PRODUCTS' #2200 Rubberized Aluminum Flashing Cement is an unsurpassed top notch flashing compound with highly reflective qualities as well as having a superior elasticity. With its high rubber content, 2200 remains resilient and flexible giving the best protection against moisture and corrosion. Manufactured with high grade oxidized base asphalts for a true cure, 2200 forms a heavy expandable brilliant silvery finish that preserves, prevents rust, inhibits fungus and reflects over 60% of the sun's damaging rays while reducing interior temperatures.

Fortified with SBS rubber. May be used to repair modified asphalt sheets as well as conventional roofing. Not for use on coal tar roofs. Covers about 12sq. ft., 1/8" thick per gallon. Area should be clean and free of foreign matter before application.

PREPARATION: Surface must be free from rust or any other foreign matter that would interfere with a good bond. Remove rust with a wire brush. For best results in cold weather, store at room temperature for 24 hours prior to application

APPLICATION: Use a trowel, putty knife or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1/8" to 1/4" thick. Apply and work cement into break or crack, then apply cement 2" - 4" beyond the problem area feathering the edges. If problem area is over 1/4" wide or 2" long embed fabric to reinforce cement then cover with additional cement.

COVERAGE: Apply at a minimum rate of 1/8". Approximate coverage is 12 square feet per gallon.

PRECAUTIONS: DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. USE ONLY WITH ADEQUATE VENTILATION! Avoid contact with skin and breathing of vapor. CLOSE AIR INTAKES on roof until solvents dissipate. KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 250 G/L

CONSISTENCY — Thick Bright Aluminum Mastic

WEIGHT — 9.3 lbs. per gal

FLASH POINT (T.C.C.) — 105°F+

SERVICE TEMPERATURE (Range) — 40°F - 90°F

RESISTANCE TO ACIDS, ALKYDS — Excellent

**ASTM
D-4586**

www.tropicalroofingproducts.com



FLORIDA
1904 SW 31st Ave.
Hallandale, FL 33009
fax: 954.963.2033
toll-free: 800.432.2855

CALIFORNIA
14435 Macaw Street
La Mirada, CA 90638
fax: 714.670.1605
toll-free: 877.827.2622

TEXAS
1225 Brai Drive, P.O. Box 5335
Port Arthur, TX 77640
fax: 409.727.4647
toll-free: 866.727.0091