



# #973 SEBS ALUMINUM BLOCKER BASE COAT

**TROPICAL ROOFING PRODUCTS' #973 SEBS Aluminum Blocker Base Coat** is a single component block copolymer elastomeric fluid applied stain blocking base coat. #973 needs no intermixing, is easy to apply, and has a highly reflective surface appearance. #973 SEBS Aluminum Blocker Base Coat is specifically formulated to prevent asphalt bleed-through on applications over BUR, SBS, and APP.

**PREPARATION:** Pressure washing of the entire existing substrate should be performed at a minimum rate of 2,000 psi. All surfaces to be coated with #973 shall be clean, dry, and free from dirt, oil, grease and rust.

**APPLICATION:** Recommended application of #973 SEBS Aluminum Blocker Base Coat is by brush, roller, or spray. Apply one gallon per 100 square feet. Always allow base coat to completely dry before proceeding to the application of the finish coat of #972 SEBS Elastomeric Roof Coating. Do not thin. Apply at a minimum temperature of 45° F. A complete cure will take between 12-24 hours depending on temperature and humidity.

**CARE OF EQUIPMENT:** Equipment and tools may be cleaned with petroleum solvents, mineral spirits, or paint thinner. Take necessary precautions when handling combustible material.

**PRECAUTIONS:** Keep away from heat, sparks, and open flame. In interior areas, provide for proper ventilation or respiratory equipment. Use proper safety equipment.

**WARNING:** Avoid breathing fumes and prolonged contact with skin. Do not take internally. **DANGER!** Harmful or fatal if swallowed. Do not induce vomiting. Call a physician immediately. Keep container covered when not in use. Do not thin. **DO NOT HEAT CONTAINER** or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

### CAUTION!

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

**MAXIMUM V.O.C = 550 G/L**  
ELONGATION — 650%  
PERMEANCE — 1.0  
VISCOSITY @ 77° F, KU— 110 +/- 5  
DENSITY(WPG) — 9.7 +/- .2

[www.tropicalroofingproducts.com](http://www.tropicalroofingproducts.com)



FLORIDA  
1904 SW 31st Ave.  
Hallandale, FL 33009  
fax: 954.963.2033  
toll-free: 800.432.2855

CALIFORNIA  
14435 Macaw Street  
La Mirada, CA 90638  
fax: 714.670.1605  
toll-free: 877.827.2622

TEXAS  
1225 Brai Drive, P.O. Box 5335  
Port Arthur, TX 77640  
fax: 409.727.4647  
toll-free: 866.727.0091