



#975 SEBS ELASTOMERIC FLASHING MASTIC

TROPICAL ROOFING PRODUCTS' #975 SEBS Elastomeric Flashing Mastic is a single component block copolymer elastomeric mastic that forms a tough and durable elastomeric membrane. The mastic has exceptional elongation properties, cold weather pliability, excellent weather and water resistance, good chemical resistance, and is highly reflective.

USES: #975 SEBS Elastomeric Flashing Mastic works great to patch and repair existing EPDM, APP, SBS, BUR, PVC, Hypalon, fiberglass, concrete, and wood. #975 also makes an excellent sealant for horizontal and vertical seams and joints in a metal roofing system. The mastic also seals screw heads, fasteners, vents, and other protrusions and penetrations.

PREPARATION: All surfaces to receive mastic must be clean, dry, and free from dirt, oil, grease, and all other foreign matter. Prime rusted areas with Tropical Roofing Products #960 Eternalastic Metal Primer (at rate of one gallon per 100 sq.ft.) and let it dry, before applying mastic. Always allow mastic to thoroughly cure before applying the base coat if applying a coating system.

APPLICATION: #975 SEBS Elastomeric Flashing Mastic may be applied by brush or trowel. When applying mastic with polyester membrane follow the first three steps.

1. Apply first coat of mastic at rate of 1/16" nominal thickness by the width of the selected membrane.
2. While mastic is still wet, embed the membrane in the mastic and keep smooth; there must not be any wrinkles, fish mouths, or bridging of the fabric.
3. Apply final coat of mastic at a rate of 1/16" thickness to totally cover the membrane. No membrane should be visible upon completion of the second coat of mastic. Coverage rates will vary depending on the size of the fabric and the profile of the roof. (On average using 6" fabric, one gallon of mastic will cover 25-30 linear feet, including both coats of mastic.)
4. All screw heads and fasteners should be encapsulated in mastic.
5. In a coating system, allow mastic to completely cure prior to application of base coat. Cure times will vary depending on temperature and humidity.

CARE OF EQUIPMENT: Equipment and tools may be cleaned with petroleum solvents, mineral spirits, or paint thinner. Take necessary precautions when handling combustible material.

PRECAUTIONS: Keep away from heat, sparks, and open flame. In interior areas, provide for proper ventilation or respiratory equipment. Use proper safety equipment.

WARNING: Avoid breathing fumes and prolonged contact with skin. Do not take internally. **DANGER!** Harmful or fatal if swallowed. Do not induce vomiting. Call a physician immediately. Keep container covered when not in use. Do not thin. **DO NOT HEAT CONTAINER** or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CAUTION! COMBUSTIBLE!

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY!
If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

MAXIMUM V.O.C = 550 G/L
ELONGATION — 350%
DENSITY(WPG) — 9.7
TENSILE STRENGTH, PSI — 1600
SOLIDS, % BY WEIGHT — 66%

www.tropicalroofingproducts.com



FLORIDA
1904 SW 31st Ave.
Hallandale, FL 33009
fax: 954.963.2033
toll-free: 800.432.2855

CALIFORNIA
14435 Macaw Street
La Mirada, CA 90638
fax: 714.670.1605
toll-free: 877.827.2622

TEXAS
1225 Brai Drive, P.O. Box 5335
Port Arthur, TX 77640
fax: 409.727.4647
toll-free: 866.727.0091