



# #501 ALL WEATHER PREMIUM ROOF MASTIC

**TROPICAL ROOFING PRODUCTS' #501 All Weather Premium Roof Mastic** is a top notch, superior grade mastic that adheres to all surfaces wet or dry. #501's unique formulation is designed for repairing leaks, cracked spots, holes in shingles, concrete, and steel or metal roofs. #501 can be used on all flashings around skylights, gutters, and in all crevices. #501 is ready to use as it comes out of the can and can be applied with a trowel or knife. #501 is a carefully mixed homogeneous blend of high-grade fibers, select asphalt, minerals, plasticizers, and aromatic hydrocarbons. #501 readily adheres to all prepared surfaces. #501 will not sag, slip or mudcrack, and will remain highly resilient and durable through all seasons.

**PREPARATION:** Surface must be clean and free from rust or any other foreign matter that would interfere with a good bond. For best results in cold weather, store at room temperature for 24 hours prior to application.

**APPLICATION:** Use a trowel, putty knife, or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1/8" to 1/4" thick. Apply and work cement into break or crack, then apply cement 2"-4" beyond the problem area feathering the edges. Embed fabric to reinforce cement, then cover with additional cement, if problem area is over 1/4" wide or 2" long.

**COVERAGE:** Apply at a minimum rate of 1/8". Approximate coverage 12 square feet per gallon.

**PRECAUTIONS:** DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

**CLEANUP:** Clean tools with mineral spirits or paint thinner.

### CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. USE ONLY WITH ADEQUATE VENTILATION! Avoid contact with skin and breathing of vapor. CLOSE AIR INTAKES on roof until solvents dissipate. KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Contains volatile solvents that might contaminate potable water.

#### MAXIMUM V.O.C = 250 G/L

CONSISTENCY — Thick Mastic, Apply by Trowel  
WEIGHT — 8.7 lbs. per gal +/- .2  
FLASH POINT (T.C.C.) — 105°F+  
SERVICE TEMPERATURE (Range) — 40°F-90°F  
RESISTANCE TO ACIDS, ALKALYS — Excellent

ASTM  
D-4586  
D-3409

[www.tropicalroofingproducts.com](http://www.tropicalroofingproducts.com)



FLORIDA  
1904 SW 31st Ave.  
Hallandale, FL 33009  
fax: 954.963.2033  
toll-free: 800.432.2855

CALIFORNIA  
14435 Macaw Street  
La Mirada, CA 90638  
fax: 714.670.1605  
toll-free: 877.827.2622

TEXAS  
1225 Brai Drive, P.O. Box 5335  
Port Arthur, TX 77640  
fax: 409.727.4647  
toll-free: 866.727.0091

