



### SECTION

#### NOTES:

1. PREPARE ALL ROOF SURFACES AS REQUIRED BY THE FLUID APPLIED SYSTEM MANUFACTURER
2. IF RUST IS PRESENT, PRIME ENTIRE ROOF WITH #960 PRIMER @ 200 SF/GAL MIN. COVERAGE
3. REMOVE LOOSE OR DAMAGED FASTENERS AND REPLACE WITH FASTENERS DESIGNED TO PENETRATE THE DECK AND SUPPORTING MEMBERS WITH NEOPRENE WASHERS AT THE SCREW HEAD.
4. DECK CONFIGURATIONS MAY DIFFER FROM THE DECK PROFILE INDICATED, BUT THE APPLICATION SHALL REMAIN SIMILAR.
5. FLUID APPLIED RESTORATION COATING SYSTEM – BASE COAT, REINFORCED FABRIC, BASE COAT 2, AND FINISH COAT COMPONENTS. ALL VERTICAL SEAMS ARE TREATED WITH BASE COAT AND 4", 6" OR 8" FABRIC DEPENDING ON ROOF PROFILE. HORIZONTAL SEAMS ARE COVERED WITH 12" FABRIC AND BASE COAT. ALL FASTENERS ARE TREATED WITH #950/951 MASTIC (ACRYLIC) OR #9100 MASTIC (SILICONE)
6. BASE COAT – COMBINED COVERAGE (2 COATS) AT A MINIMUM RATE AS DIRECTED IN THE SPECIFICATION.
7. EACH FINISH COAT SHALL BE APPLIED AT THE PRODUCT DATA SHEET RECOMMENDATIONS. ALLOW TO DRY BETWEEN COATS.
8. PRIMING – REFER TO TROPICAL ROOFING PRODUCTS SPECIFICATIONS FOR DECK PRIMING REQUIREMENTS.

NOTE: FOR SPECIFIC PRODUCT RECOMMENDATION REFER TO THE APPROPRIATE FLUID APPLIED SYSTEM GUIDE SPECIFICATIONS AT [WWW.TROPICALROOFINGPRODUCTS.COM](http://WWW.TROPICALROOFINGPRODUCTS.COM)



## FLUID APPLIED RESTORATION COATING SYSTEM

### SECTION AT METAL PANEL SEAM DETAIL

DATE :

12-13-16

DETAIL NO :

10