



#202 FIBERED ROOF COATING

TROPICAL ROOFING PRODUCTS' #202 FIBERED ROOF COATING is a durable fiber reinforced Asphalt solvent-based waterproof coating providing excellent weathering protection for smooth or granulated built up roofing membranes. Also effective for adhering roofing granules to the surface. More flexible than hot asphalt in cold weather. #202 Fibered Roof Coating meets and exceeds all the requirements of ASTM D 4479 and Miami-Dade NOA.

PREPARATION: All surfaces must be clean, dry, smooth, even, and free from all other foreign matter. Raised edges, buckles, and blisters should be cut and flattened. Check flashings, drains, edgings, vents, and valleys and repair as needed. Local building codes, roof deck condition, or moisture in old roof may indicate complete removal of an old roof.

APPLICATION: Apply to clean dry surface using stiff bristle brush, roller, or spray equipment. For best results, weather should be at least 65°F, dry and clear, with no threat of rain for 48 hours. Drying time is approximately 48 hours in warm, dry weather. For spray applications use #202 Spray Grade Fibered Roof Coating.

COVERAGE: Apply at the rate of approximately 2 to 4 gallons per 100 sq. ft. depending on job specifications. Stir coating to uniform consistency before using. Avoid heavy mounds of mass accumulation.

PRECAUTIONS: DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. USE ONLY WITH ADEQUATE VENTILATION! Avoid contact with skin and breathing of vapor. CLOSE AIR INTAKES on roof until solvents dissipate. KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 250 G/L
CONSISTENCY — THICK BLACK LIQUID
WEIGHT — 7.8 LBS. PER GAL
FLASH POINT (T.C.C.) — 107°F+
DRYING TIME — AVERAGE: 2-5 HRS. TO TOUCH

ASTM D 4479



FLORIDA
1904 SW 31ST AVE
HALLANDALE, FL 33009
800.432.2855

CALIFORNIA
14435 MACAW STREET
LA MIRADA, CA 90638
877.827.2622

TEXAS
1225 BRAI DRIVE
PORT ARTHUR, TX 77640
866.727.0091