



#996 ETERNA-SIL PREMIUM ASPHALT BLEED BLOCKER

TROPICAL ROOFING PRODUCTS' #996 ETERNA-SIL PREMIUM ASPHALT BLEED BLOCKER is a highly engineered acrylic single-component, water-based primer designed for application over BUR, Mod-Bit, and smooth or mineral surfaced cap sheet. #996 is designed specifically to prevent asphalt bleed-through when applying Silicone coating systems over all asphalt substrates. #996 requires no inter-mixing and delivers fast-dry performance.

FEATURES/BENEFITS: • Fast dry • Low VOC • Single component material • Excellent adhesion
• No inter-mixing required. • Water-based • Easy to apply by spray, brush or roller

PRODUCT LIMITATIONS: #996 should not be applied to wet, dusty, oily, mildewed, heavily chalked, blistered or otherwise structurally unsound surfaces. Do not apply #996 over Silicone.

PREPARATION: All surfaces to be coated must be clean, dry, and paintable. It may be necessary to power wash enhance adhesion. See application specification for more details.

MIXING PROCEDURES: #996 should be lightly hand-mixed to uniformity prior to application.

APPLICATION EQUIPMENT: #996 can be applied by brush, roller or spray.

APPLICATION: For ideal drying conditions, apply on warm, sunny days, preferably in the morning hours to provide maximum dry time. #996 can be applied to a dry or slightly damp, but not wet, surface. Water must be swept out of all puddles prior to application of #996. Stir thoroughly before application to achieve a uniform consistency. Apply with a brush, heavy-duty paint roller or heavy-duty spray equipment. Under normal conditions, #996 will dry in 4 – 6 hours. Relative humidity and temperature will directly affect drying time. Avoid over application.

COVERAGE: Apply at a rate of 1.5 - 2.0 gallon per 100 sq. feet per coat dependent upon roof porosity.

PRECAUTIONS: DO NOT APPLY IF TEMPERATURE IS BELOW 50° F OR ABOVE 110°F. DO NOT APPLY IF THERE IS A THREAT OF RAIN OR DEW WITHIN 48–72 HOURS. DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur.

CLEANUP: Clean wet coating from hands and tools with soap and water. Dried coating on tools can be cleaned with mineral spirits or paint thinner.

PACKAGE SIZES: Available in 5-gallon pails and 55-gallon drums.

CAUTION!

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! Always refer to the SDS located at www.tropicalroofingproducts.com

VOC = <50g/l
Initial Viscosity (cPs) = 6,000 - 8,000
Density = 8.80 – 9.1 lbs./gal
% Solids = 40 % +/- 2%
pH = 9.5 - 10.0

FLORIDA
1904 SW 31ST AVE
HALLANDALE, FL 33009
800.432.2855

CALIFORNIA
14435 MACAW STREET
LA MIRADA, CA 90638
877.827.2622

TEXAS
1225 BRAI DRIVE
PORT ARTHUR, TX 77640
866.727.0091