



## #100 PLASTIC ROOF CEMENT

**TROPICAL ROOFING PRODUCTS' #100 Plastic Roof Cement** is a multi-purpose heavy consistency Plastic Cement for repairing leaks, cracked spots, holes in shingles, concrete and steel or metal roofs. #100 can be used on flashings around skylights, gutters, and in most crevices. #100 is ready to use as it comes out of the pail and can be applied with a trowel or knife. #100 readily adheres to most prepared surfaces and will not sag, slip, or mud crack, and will remain highly resilient and durable through all seasons when properly applied.

**PREPARATION:** Surface must be clean and free from rust or any other foreign matter that would interfere with a good bond. Remove rust with a wire brush. For best results in cold weather, store at room temperature for 24 hours prior to application

**APPLICATION:** Use a trowel, putty knife or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1/8" to 1/4" thick. Apply and work cement into break or crack, then apply cement 2" - 4" beyond the problem area feathering the edges. Embed glass fabric to reinforce cement, and then cover with additional cement, if problem area is over 1/4" wide or 2" long.

**COVERAGE:** Apply at a minimum rate of 40 linear ft. per gallon with 4" wide 1/8" thick application.

**PRECAUTIONS: DO NOT THIN. DO NOT HEAT CONTAINER** or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

**CLEANUP:** Clean tools with mineral spirits or paint thinner.

### CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. **USE ONLY WITH ADEQUATE VENTILATION!** Avoid contact with skin and breathing of vapor. **CLOSE AIR INTAKES** on roof until solvents dissipate. **KEEP OUT OF REACH OF CHILDREN.** Close container after each use. **DO NOT TAKE INTERNALLY!** If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY!** Contains volatile solvents that might contaminate potable water

- **MAXIMUM V.O.C. = 250 G/L**
- **CONSSTENCY – THICK SOFT MASTIC**
- **WEIGHT – 8.7 LBS PER GAL**
- **FLASH POINT (T.C.C.) – 105° F+**
- **SERVICE TEMPERATURE (RANGE) – 40°F – 90°F**
- **RESISTANCE TO ACIDS, ALKYDS - EXCELLENT**



FLORIDA  
1904 SW 31ST AVE  
HALLANDALE, FL 33009  
800.432.2855

CALIFORNIA  
14435 MACAW STREET  
LA MIRADA, CA 90638  
877.827.2622

TEXAS  
1225 BRAI DRIVE  
PORT ARTHUR, TX 77640  
866.727.0091