



#2100 ALL WEATHER RUBBERIZED FLASHING CEMENT

TROPICAL ROOFING PRODUCTS " Best-in-Class " #2100 ALL WEATHER/ALL SEASON Rubberized Heavy Duty Commercial FLASHING CEMENT is specifically formulated for the professional roofer. #2100 ALL WEATHER /ALL SEASON FLASHING CEMENT provides strong adhesion to wet and dry surfaces. Will bond under water for permanent repairs. #2100 ALL WEATHER/ALL SEASON Heavy Duty Commercial flashing compound is manufactured with superior oxidized asphalts for extreme durability. With its high SBS rubber content and fortified with **Power Gel Technology**, #2100 will remain highly resilient, flexible and durable through all seasons. Special surfactants make this product adhere to most surfaces in wet or dry conditions. #2100 is the premier repair compound that is easily spread and applied to repair splits, seams, cracks and holes in spudded gravel, mineral surfaced cap sheet, smooth surface asphalt roofs, and most SBS and Granulated APP membranes. It will seal areas around skylights, chimneys, vent pipes, gravel guards, down spouts, cracks in concrete and control joints on roofs. This product is an excellent utility mastic for use below grade. Will not run, slip, sag, or mud crack. Formulated with a high softening point oxidized asphalt for superior high temperature resistance.

Recommended for flat commercial roofs, in locations where roof is exposed to high heat, such as heater vent pipes, and is excellent for repairs on conventional BUR membranes where movement is expected to occur.

RECOMENDED SUBSTRATE APPLICATION - APP GRANULAR MEMBRANE, TILE & METAL.

NOT RECOMENDED FOR SHINGLES. Meets ASTM D 4586 and ASTM D 3409. Miami-Dade NOA Compliant.

PREPARATION: Surface must be clean and free from rust or any other foreign matter that would interfere with a good bond. For best results in cold weather, store at room temperature for 24 hours prior to application.

APPLICATION: Use a trowel, putty knife or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1/8" to 1/4" thick. Apply and work cement into break or crack, then apply cement 2"-4" beyond the problem area feathering the edges. Embed fabric to reinforce cement, then cover with additional cement, if problem area is over 1/4" wide or 2" long.

COVERAGE: Apply at a minimum rate of 40 linear ft. per gallon with 4" wide 1/8" thick application.

PRECAUTIONS: DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight, and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

Contains petroleum distillate. Keep away from heat and flame. **USE ONLY WITH ADEQUATE VENTILATION!** Avoid contact with skin and breathing of vapor. **CLOSE AIR INTAKES** on roof until solvents dissipate. **KEEP OUT OF REACH OF CHILDREN.** Close container after each use. **DO NOT TAKE INTERNALLY!** If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY!** Contains volatile solvents that might contaminate potable water.

CAUTION! COMBUSTIBLE!

MAXIMUM V.O.C = 250 G/L
CONSISTENCY — THICK SOFT MASTIC
WEIGHT — 8.7 LBS. PER GAL
FLASH POINT (T.C.C.) — 105°F+
SERVICE TEMPERATURE (RANGE) — 40°F - 90°F
RESISTANCE TO ACIDS, ALKYDS — EXCELLENT

ASTM D 4586
ASTM D 3409



FLORIDA
1904 SW 31ST AVE
HALLANDALE, FL 33009
800.535.6947

CALIFORNIA
14435 MACAW STREET
LA MIRADA, CA 90638
877.827.2622

TEXAS
1225 BRAI DRIVE
PORT ARTHUR, TX 77640
866.727.0091