



#4003 FIBERED ROOF RESATURANT & SEALER

TROPICAL ROOFING PRODUCTS' #4003 FIBERED ROOF RE-SATURANT & SEALER is a carefully prepared blend of selected asphalt, mineral fillers and penetrating oils that soak into the existing asphalt roof system to revitalize and help restore the old roof. Forms a continuous durable seal resistant to cracking and splitting under most conditions. Meets ASTM D 4479. Miami-Dade NOA Compliant.

PREPARATION: All surfaces must be clean, dry, smooth, even, and free from all other foreign matter. Raised edges, buckles, and blisters should be cut and flattened. Check flashings, drains, edgings, vents, and valleys and repair as needed.

APPLICATION: Apply to clean dry surface using stiff, bristle brush, roller, or spray equipment. For best results, weather should be at least 65°F, dry and clear, with no threat of rain for 48 hours. Drying time is approximately 48 hours in warm, dry weather.

COVERAGE: Apply at the rate of approximately 3 gallons per 100 square feet depending on job specifications. Stir coating to uniform consistency before using. Avoid heavy mounds of mass accumulation.

PRECAUTIONS: DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. **USE ONLY WITH ADEQUATE VENTILATION!** Avoid contact with skin and breathing of vapor. **CLOSE AIR INTAKES** on roof until solvents dissipate. **KEEP OUT OF REACH OF CHILDREN.** Close container after each use. **DO NOT TAKE INTERNALLY!** If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY!** Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 300 G/L
CONSISTENCY — THICK BLACK LIQUID
WEIGHT — 8.8 LBS. PER GAL
FLASH POINT (T.C.C.) — 105°F+
SERVICE TEMPERATURE (RANGE) — 40°F - 90°F
DRYING TIME — AVERAGE: 2-5 HOURS

ASTM D 4479



FLORIDA
1904 SW 31ST AVE
HALLANDALE, FL 33009
800.432.2855

CALIFORNIA
14435 MACAW STREET
LA MIRADA, CA 90638
877.827.2622

TEXAS
1225 BRAI DRIVE
PORT ARTHUR, TX 77640
866.727.0091