



#508 WET SURFACE MODIFIED MASTIC

TROPICAL ROOFING PRODUCTS' #508 WET SURFACE MODIFIED MASTIC is a dependable rubber modified soft and pliable mastic specially formulated for superior adhesion under severe cold and or wet surface conditions, even in driving rain or under water. #508's unique formulation is designed for repairing leaks, cracked spots, holes in shingles, concrete, and steel or metal roofs. Fortified with **Power Gel Technology** so it will remain highly resilient and durable through all seasons. Meets ASTM D 4586 and ASTM D 3409.

PREPARATION: Surface must be free from rust or any other foreign matter that would interfere with a good bond. Remove rust with a wire brush. For best results in cold weather, store at room temperature for 24 hours prior to application.

APPLICATION: Use a trowel, putty knife or gloved hand to repair cracks, tears, holes, and breaks by applying cement 1/8" to 1/4" thick. Apply and work cement into break or crack, then apply cement 2" – 4" beyond the problem area feathering the edges. If problem area is over 1/4" wide or 2" long embed glass fabric to reinforce cement then cover with additional cement.

COVERAGE: Approximate coverage is 12 square feet per gallon. Apply at a minimum rate of 40 linear ft. per gallon with 4" wide 1/8" thick application.

PRECAUTIONS: DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur.

CLEANUP: Clean tools with mineral spirits or paint thinner

CAUTION! COMBUSTIBLE!

Contains petroleum distillate. Keep away from heat and flame. **USE ONLY WITH ADEQUATE VENTILATION!** Avoid contact with skin and breathing of vapor. **CLOSE AIR INTAKES** on roof until solvents dissipate. **KEEP OUT OF REACH OF CHILDREN.** Close container after each use. **DO NOT TAKE INTERNALLY!** If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY!** Contains volatile solvents that might contaminate potable water.

MAXIMUM V.O.C = 250 G/L
CONSISTENCY — THICK SOFT MASTIC
WEIGHT — 8.7 LBS. PER GAL
FLASH POINT (T.C.C.) — 105°F+
SERVICE TEMPERATURE (RANGE) — 40°F - 90°F
RESISTANCE TO ACIDS, ALKYDS — EXCELLENT

ASTM D 4586
ASTM D 3409



FLORIDA
1904 SW 31ST AVE
HALLANDALE, FL 33009
800.432.2855

CALIFORNIA
14435 MACAW STREET
LA MIRADA, CA 90638
877.827.2622

TEXAS
1225 BRAI DRIVE
PORT ARTHUR, TX 77640
866.727.0091