



#921Q EARLY RAIN-RESISTANT COATING

TROPICAL ROOFING PRODUCTS' #921Q EARLY RAIN-RESISTANT COATING is a California Title 24 Part 6 compliant, acrylic elastomeric roof coating that is formulated to resist wash off from rain within 45 minutes after application. Where traditional acrylic coatings may fail in higher humidity environments or when rain is on the horizon, 921Q will perform and extend the window of application. 921Q will adhere to most common roofing substrates including Mod Bit, APP, PVC, and SPUF.

PREPARATION

Surface must be clean and dry, free of moisture both on and beneath the surface. Pressure wash roof thoroughly to remove as much dust, dirt, and debris as possible. After careful inspection of entire roof, repair all holes, cracks, tears or breaks with reinforcing fabric and #950 Eternamastic. #950 Eternamastic repairs can usually be coated within 24 hours. Coat newly applied asphalt emulsion as soon as the emulsion can take foot traffic without scuffing the surface, normally 7–10 days.

APPLICATION

Apply on warm, sunny days, preferably in the morning hours to provide maximum cure time. #921Q must be applied to a dry surface. Water must be swept out of all puddles prior to application of #921Q. Mix #921Q thoroughly before application to achieve a uniform consistency. Apply with a heavy-duty paint roller or heavy-duty spray equipment. When applied with roller or brush, strokes should be kept in one direction. Apply second coat perpendicular to the first. Allow at least four hours between coats and 24–48 hours for full cure, dependent upon weather conditions. Relative humidity will directly affect drying/curing time.

DO NOT APPLY TO FLAT SURFACES WITH POOR DRAINAGE OR WHERE PONDING WATER WILL EXIST

COVERAGE RATE

Apply at a minimum rate of 1-1.5 gallons per 100 sq. feet per coat dependent upon roof porosity. Two coats are required to achieve optimal performance of the coating.

PRECAUTIONS

DO NOT APPLY IF TEMPERATURE IS BELOW 50° F OR ABOVE 110°F. DO NOT APPLY IF THERE IS A THREAT OF RAIN OR DEW WITHIN 48–72 HOURS. DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur. This coating is not recommended for areas with inadequate drainage (ponding water), over gravel, over walking decks, or old roofs that are too brittle and dry.

CLEANUP

Clean tools with soap and water or Tropical's #651 UltraClean

CAUTION!

KEEP OUT OF REACH OF CHILDREN. Close container after each use.

DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

WET WEIGHT — 11.47 LBS PER GAL

DRY WEIGHT — 7.57 LBS PER GAL

INITIAL ELONGATION % — 336%

INITIAL TENSILE STRENGTH — 215 PSI

VOLUME SOLIDS — 51%

WEIGHT SOLIDS — 66%

FLORIDA
1904 SW 31ST AVE
HALLANDALE, FL, 33009
800.432.2855

CALIFORNIA
14435 MACAW ST
LA MIRADA, CA, 90638
877.827.2622

TEXAS
1225 BRAI DR
PORT ARTHUR, TX, 77640
866.727.0091

PACIFIC NORTHWEST
14325 NE AIRPORT WAY, SUITE 107
PORTLAND, OR, 97230
844.854.9323