

Seal the Deal

TRP-1

VOC

UltraSeal



Advanced MS Polymer
Hybrid Sealant Adhesive

TABLE 2: TYPICAL CURED PROPERTIES*
(AFTER 14 DAYS CURE AT 77°F AND 50% RH)

Property	Value	Test Method/Note
Hardness (Shore A)	38	ASTM D 2240
Modulus @ 100% Elongation	70 psi	ASTM D 412
Tensile Strength @ Break	180 psi	ASTM D 412
Elongation @ Break	950%	ASTM D 412
Adhesion Peel	>35 piw	TT-S-00230C/ASTM C 794
Joint Movement Capability	+/-50%	TT-S-00230C / ASTM C 719
UV Resistance	Pass	ASTM C 793

COVERAGE FOR 9.5 FL OZ (298 ML) CARTRIDGE

Depth	Width							
	1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
1/8"	99	49	33	24	20	16	14	12
1/4"		24	20	12	10	8	7	6
3/8"			11	8	6	5	5	4
1/2"				6	5	4	3	3

LINEAR FEET PER 9.5 FL OZ CARTRIDGE