



202 FIBERED ROOF COATING

APPLICATION METHODS



Application rate at 2-4 gallons per 100 square feet. Application rates will vary by surface, porosity, and job conditions. Please consult Tropical Roofing Products for total dry film thickness requirements.

AVAILABLE SIZES



#202 Fibered Roof Coating is a durable fiber reinforced Asphalt solvent-based waterproof coating providing excellent weathering protection for smooth or granulated built up roofing membranes. Also effective for adhering roofing granules to the surface. More flexible than hot asphalt in cold weather. #202 Fibered Roof Coating meets and exceeds all the requirements of ASTM D 4479.





PRODUCT DESCRIPTION

#202 Fibered Roof Coating is a durable fiber reinforced Asphalt solvent-based waterproof coating providing excellent weathering protection for smooth or granulated built up roofing membranes. Also effective for adhering roofing granules to the surface. More flexible than hot asphalt in cold weather. **#202 Fibered Roof Coating** meets and exceeds all the requirements of ASTM D 4479.

FEATURES + BENEFITS

- Certified to Meet ASTM D 4479
- Durable Fiber Reinforced Asphalt Solvent-Based Waterproof Coating
- Excellent Weathering Protection for Smooth or Granulated BUR
- More Flexible than Hot Asphalt in Cold Weather

PHYSICAL PROPERTIES

Maximum V.O.C.	250 g/L
Consistency	Thick Black Liquid
Weight	7.8 lbs./gal

Flash Point (TCC)	107°F
Drying Time Average	2-5 hours to touch

PREPARATION

All surfaces must be clean, dry, smooth, even, and free from all other foreign matter. Raised edges, buckles, and blisters should be cut and flattened. Check flashings, drains, edgings, vents, and valleys and repair as needed. Local building codes, roof deck condition, or moisture in old roof may indicate complete removal of an old roof.

APPLICATION

Apply to clean dry surface using stiff bristle brush, roller, or spray equipment. For best results, weather should be at least 65°F, dry and clear, with no threat of rain for 48 hours. Drying time is approximately 48 hours in warm, dry weather. For spray applications use **#202 Spray Grade Fibered Roof Coating**.

COVERAGE

Apply at the rate of approximately 2-4 gallons per 100 square feet depending on job specifications. Stir coating to uniform consistency before using. Avoid heavy mounds of mass accumulation.

PRECAUTIONS:

DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure lid is tight and pail is secure when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage to occur.

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!



To the best of our knowledge, all technical data contained herein is true and accurate as of the date of the issuance and subject to change without prior notice. User must contact TROPICAL ROOFING PRODUCTS (TRP) to verify correctness before specifying or ordering. We guarantee our product to conform to the quality control standards established by TRP. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY TRP EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.