



996 ETERNA-SIL PREMIUM BLEED BLOCKER

APPLICATION METHODS



Application rate at a minimum of 1.5 gallons per 100 square feet. Application rates will vary by surface, porosity, and job conditions. Please consult Tropical Roofing Products for total dry film thickness requirements.

AVAILABLE SIZES



AVAILABLE STANDARD COLORS



Pastel Green



#996 Eterna-Sil Premium Asphalt Bleed Blocker is a highly engineered acrylic single-component, water-based primer designed for application over BUR, Mod-Bit, and smooth or mineral surfaced cap sheet. **#996** is designed specifically to prevent asphalt bleed-through when applying Silicone coating systems over all asphalt substrates. **#996** requires no inter-mixing and delivers fast-dry performance.





#996 ETERNA-SIL PREMIUM BLEED BLOCKER

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

#996 Eterna-Sil Premium Asphalt Bleed Blocker is a highly engineered acrylic single-component, water-based primer designed for application over BUR, Mod-Bit, and smooth or mineral surfaced cap sheet. #996 is designed specifically to prevent asphalt bleed-through when applying Silicone coating systems over all asphalt substrates. #996 requires no inter-mixing and delivers fast-dry performance.

FEATURES + BENEFITS

- Single Component Asphalt Bleed Blocker
- Low VOC
- Fast Dry
- Excellent Adhesion
- No Inter-mixing Required

PRODUCT LIMITATIONS

#996 should not be applied to wet, dusty, oily, mildewed, heavily chalked, blistered or otherwise structurally unsound surfaces. Do not apply #996 over Silicone.

PHYSICAL PROPERTIES

Color	Light Green, Translucent
V.O.C	<50 g/L

PREPARATION

All surfaces to be coated must be clean, dry, and paintable. It may be necessary to power wash enhance adhesion. See application specification for more details.

APPLICATION EQUIPMENT

#996 can be applied by brush, roller or spray.

APPLICATION

For ideal drying conditions, apply on warm, sunny days, preferably in the morning hours to provide maximum dry time. #996 can be applied to a dry or slightly damp, but not wet, surface. Water must be swept out of all puddles prior to application of #996. Stir thoroughly before application to achieve a uniform consistency. Apply with a brush, heavy-duty paint roller or heavy-duty spray equipment. Under normal conditions, #996 will dry in 4 – 6 hours. Relative humidity and temperature will directly affect drying time. Avoid over application.

COVERAGE

Apply at a rate of 1.5- 2.0 gallon per 100 sq. feet per coat dependent upon roof porosity.

Density	10.5 – 11.5 lbs./gal
Solids by Volume	44%

PRECAUTIONS

DO NOT APPLY IF TEMPERATURE IS BELOW 50° F OR ABOVE 110°F. DO NOT APPLY IF THERE IS A THREAT OF RAIN OR DEW WITHIN 48-72 HOURS. DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur.

CLEANUP

Clean wet coating from hands and tools with soap and water. Dried coating on tools can be cleaned with mineral spirits or paint thinner.

PACKAGE SIZES

Available in 5-gallon pails and 55-gallon drums.

SHIPPING INFORMATION

D.O.T. Classification: Roof Coating, Not Regulated NFMC #170080

CONTAINER SIZE	CLASS
5 Gal.	55
55 Gal.	5



KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY!
If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of the issuance and subject to change without prior notice. User must contact TROPICAL ROOFING PRODUCTS (TRP) to verify correctness before specifying or ordering. We guarantee our product to conform to the quality control standards established by TRP. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY TRP EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.